

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
17 May 2001 (17.05.2001)

PCT

(10) International Publication Number
WO 01/34665 A1

- (51) International Patent Classification⁷: C08F 10/00, 4/70, 4/80, 4/26
- (21) International Application Number: PCT/US00/30773
- (22) International Filing Date:
9 November 2000 (09.11.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/165,265 12 November 1999 (12.11.1999) US
- (71) Applicant (for all designated States except US): E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1107 Market Street, Wilmington, DE 19898 (US).
- (72) Inventor; and
(75) Inventor/Applicant (for US only): TEASLEY, Mark, F. [US/US]; 118 Eden Road, Landenberg, PA 19350 (US).
- (74) Agent: LERMAN, Bart, E.; E.I. Du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).
- (81) Designated States (national): AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— With international search report.
— Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 01/34665 A1

(54) Title: CHAIN TRANSFER AGENTS FOR OLEFIN POLYMERIZATION

(57) Abstract: 1,4-Cyclohexadienes and triarylmethanes are chain transfer agents for certain late transition metal complex catalyzed polymerizations of olefins.

TITLE

CHAIN TRANSFER AGENTS FOR OLEFIN POLYMERIZATION

FIELD OF THE INVENTION

5 1,4-Cyclohexadienes and triarylmethanes act as chain transfer agents ("CTA") in the polymerization of olefins in which late transition metal complexes of neutral bidentate ligands are used as a polymerization catalyst.

TECHNICAL BACKGROUND

10 Polymerization of olefins using early transition metal containing catalysts such as vanadium and zirconium is a well known and commercially important technology. In many instances it is desirable to lower the molecular weight of
15 the polyolefin that would normally be produced. For example lower molecular weight polymers are usually considered easier to melt process, since they have lower melt viscosities. While polymerization process conditions can sometimes be altered to change the molecular weight of the resulting
20 polyolefin, often a CTA such as hydrogen is deliberately added to the process to lower the polyolefin molecular weight.

 The polymerization of olefins using late transition metal containing catalysts such as nickel with selected neutral bidentate ligands is known, see for instance US5714556,
25 US5880241, US6103658 and WO00/06620, all of which are incorporated by reference herein for all purposes as if fully set forth. Methods for lowering the molecular weight of polyolefins produced in such processes are known. However,
30 the CTAs that have been reported, such as hydrogen, are not very efficient and often tend to reduce the productivity of the polymerization catalyst. Since these processes often give polyolefins with unique and valuable structures, im-

proved methods for controlling the polymer molecular weight are desirable.

WO99/61492, also incorporated by reference herein for all purposes as if fully set forth, describes the use of hydrogen and other types of compounds as CTAs for late metal transition complexes of bidentate ligands as polymerization catalysts. No mention is made of the use of the compounds described herein as CTAs.


10

SUMMARY OF THE INVENTION

This invention concerns a process for the polymerization of one or more polymerizable olefins, comprising the step of contacting, under polymerization conditions:

- (a) said one or more polymerizable olefins and
 (b) an active polymerization catalyst comprising a complex of a neutral bidentate ligand of a metal selected from the group consisting of nickel, iron and cobalt,

in the presence of an effective amount of a chain transfer agent comprising a compound selected from the group consisting of a compound of the formula (I)




and a triarylmethane of the formula R^7_3CH (II), wherein:

each of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently hydrogen, hydrocarbyl, or substituted hydrocarbyl, provided that any two of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 vicinal to one another taken together may form a ring; and

each R^7 is independently aryl or substituted aryl, provided that any two of R^7 taken together may form a ring.





This invention also concerns a process for the polymerization of one or more polymerizable olefins, comprising the step of contacting:

- (a) said one or more polymerizable olefins;
- 5 (b) an effective amount of a chain transfer agent selected from the group consisting of



and a triarylmethane of the formula R^7_3CH (II);

- (c) an active polymerization catalyst which contains a nickel, iron or cobalt complex of a ligand of the formula
- 10 (IV), (V), (VI) or (VII)



wherein:

- 15 each of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently hydrogen, hydrocarbyl, or substituted hydrocarbyl, provided that any two of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 vicinal to one another taken together may form a ring;

- each R^7 is independently aryl or substituted aryl, provided that any two of R^7 taken together may form a ring;
- 20

R^{13} and R^{16} are each independently hydrocarbyl or substituted hydrocarbyl, provided that the atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R¹⁴ and R¹⁵ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R¹⁴ and R¹⁵ taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

5 R¹⁸ is hydrocarbyl or substituted hydrocarbyl, and R²⁰ is hydrogen, hydrocarbyl or substituted hydrocarbyl or R¹⁸ and R²⁰ taken together form a ring;

R¹⁹ is hydrocarbyl or substituted hydrocarbyl, and R²¹ is hydrogen, substituted hydrocarbyl or hydrocarbyl, or R¹⁹ and
10 R²¹ taken together form a ring;

each R¹⁷ is independently hydrogen, substituted hydrocarbyl or hydrocarbyl, or two of R¹⁷ taken together form a ring;

R²² and R²³ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the atom bound to the imino
15 nitrogen atom has at least two carbon atoms bound to it;

R²⁴ and R²⁵ are each independently hydrogen, hydrocarbyl, or substituted hydrocarbyl;

each R²⁶ is independently hydrogen, hydrocarbyl or substituted hydrocarbyl;
20

R²⁷ and R³⁰ are independently hydrocarbyl or substituted hydrocarbyl; and

R²⁸ and R²⁹ are each independently hydrogen, hydrocarbyl or substituted hydrocarbyl.
25

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Herein, certain terms are used. Some of them are:

A "hydrocarbyl group" is a univalent group containing only carbon and hydrogen. As examples of hydrocarbyls may
30 be mentioned unsubstituted alkyls, cycloalkyls and aryls. If not otherwise stated, it is preferred that hydrocarbyl groups herein contain 1 to about 30 carbon atoms.

By "saturated hydrocarbyl" is meant a univalent radical that contains only carbon and hydrogen, and contains no carbon-carbon double bonds, triple bonds and aromatic groups.

By "substituted hydrocarbyl" herein is meant a hydrocarbyl group that contains one or more substituent groups which are inert under the process conditions to which the compound containing these groups is subjected (e.g., an inert functional group, see below). The substituent groups also do not substantially detrimentally interfere with the polymerization process or operation of the polymerization catalyst system. If not otherwise stated, it is preferred that substituted hydrocarbyl groups herein contain 1 to about 30 carbon atoms. Included in the meaning of "substituted" are chains or rings containing one or more heteroatoms, such as nitrogen, oxygen and/or sulfur, and the free valence of the substituted hydrocarbyl may be to the heteroatom. In a substituted hydrocarbyl, all of the hydrogens may be substituted, as in trifluoromethyl.

By "(inert) functional group" herein is meant a group, other than hydrocarbyl or substituted hydrocarbyl, that is inert under the process conditions to which the compound containing the group is subjected. The functional groups also do not substantially interfere with any process described herein that the compound in which they are present may take part in. Examples of potential functional groups include halo, ester, keto (oxo), amino, imino, carboxyl, phosphite, phosphonite, phosphine, phosphinite, thioether, amide, nitrile, and ether. Preferred functional groups are halo, ester, amino, imino, carboxyl, phosphite, phosphonite, phosphine, phosphinite, thioether, and amide. Particularly preferred examples of functional groups include halo (fluoro, chloro, bromo and iodo) and ether such as $-OR^{60}$, wherein R^{60} is hydrocarbyl or substituted hydrocarbyl. Which

substituents are useful in which polymerizations may in some cases be determined by reference to previously incorporated US5714556, US5880241, US6103658 and WO00/06620. In cases in which the functional group may be near the transitional
5 metal atom, the functional group should not coordinate to the metal atom more strongly than the groups in those compounds are shown as coordinating to the metal atom, that is they should not displace the desired coordinating group.

By "(substituted) hydrocarbylene" is meant a group
10 analogous to (substituted) hydrocarbyl, except the radical is divalent.

By "aryl" is meant a monovalent aromatic group in which the free valence is to the carbon atom of an aromatic ring. An aryl may have one or more aromatic rings which may be
15 fused, connected by single bonds or other groups.

By "phenyl" is meant the C₆H₅- radical, and a "phenyl moiety" or "substituted phenyl" is a radical in which one or more of the hydrogen atoms is replaced by a substituent group (which may include hydrocarbyl).


By "substituted aryl" is meant a monovalent aromatic
20 group substituted as set forth in the above definition of "substituted hydrocarbyl". Similar to an aryl, a substituted aryl may have one or more aromatic rings which may be fused, connected by single bonds or other groups; however,
25 when the substituted aryl has a heteroaromatic ring, the free valence in the substituted aryl group can be to a heteroatom (such as nitrogen) of the heteroaromatic ring instead of a carbon.

If not otherwise stated, hydrocarbyl, substituted hydrocarbyl and all other groups containing carbon atoms, such
30 as alkyl, preferably contain 1 to 20 carbon atoms.

By a "neutral bidentate ligand" is meant a bidentate ligand that has no charge on the ligand (is not ionic in a formal sense if not coordinated to the transition metal).


By "olefin" is meant a compound containing one or more olefinic double bonds. In the event that the compound contains more than one olefinic double bond, they should be non-conjugated. As examples of olefins may be mentioned cyclopentene, a styrene, a norbornene, and compounds of the formulas $R^{70}CH=CH_2$ and $H_2C=CH(CH_2)_sCO_2R^{71}$, wherein R^{70} is hydrogen or alkyl, R^{71} is hydrocarbyl or substituted hydrocarbyl; and s is 0 or an integer of from 1 to 20.

By a "styrene" is meant a compound of the formula



wherein R^{140} , R^{141} , R^{142} , R^{143} and R^{144} are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or a functional group, all of which are inert in the polymerization process. It is preferred that all of R^{140} , R^{141} , R^{142} , R^{143} and R^{144} are hydrogen. Styrene (itself) is a preferred styrene.

By a "norbornene" is meant ethylidene norbornene, dicyclopentadiene, or a compound of the formula



wherein R^{145} is hydrogen or hydrocarbyl containing 1 to 20 carbon atoms. It is preferred that R^{145} is hydrogen or alkyl, more preferably hydrogen or n-alkyl, and especially preferably hydrogen. The norbornene may be substituted by one or more hydrocarbyl, substituted hydrocarbyl or func-

tional groups in the R¹⁴⁵ or other positions, with the exception of the vinylic hydrogens, which remain. Norbornene (itself), dimethyl endo-norbornene-2,3-dicarboxylate, t-butyl 5-norbornene-2-carboxylate are preferred norbornenes and norbornene (itself) is especially preferred.

"Noncoordinating" ions are mentioned and useful herein. By "noncoordinating" (or "relatively noncoordinating" or "weakly coordinating") anions are meant those anions as are generally referred to in the art in this manner, and the coordinating ability of such anions is known and has been discussed in the literature. See, for instance, W. Beck et al., Chem. Rev., vol. 88, pp. 1405-1421 (1988), and S.H. Strauss, Chem. Rev., vol. 93, pp. 927-942 (1993), both of which are hereby included by reference. Among such anions are those formed from aluminum compounds (such as those described in the immediately preceding paragraph) and X⁻ (an anion as discussed in further detail below), including (R¹⁹)₃AlX⁻, (R¹⁹)₂AlClX⁻, R¹⁹AlCl₂X⁻, and R¹⁹AlOX⁻, wherein R¹⁹ is alkyl. Other useful noncoordinating anions include BAF⁻ {BAF = tetrakis[3,5-bis(trifluoromethyl)phenyl]borate}, SbF₆⁻, PF₆⁻, and BF₄⁻, trifluoromethanesulfonate, p-toluenesulfonate, (R_fSO₂)₂N⁻, and (C₆F₆)₄B⁻.

A neutral Lewis acid or a cationic Lewis or Bronsted acid whose counterion is a weakly coordinating anion may also be present as part of the catalyst system. By a "neutral Lewis acid" is meant a compound that is a Lewis acid capable of abstracting an anion from a late transition metal compound to form a weakly coordination anion. The neutral Lewis acid is originally uncharged (i.e., not ionic). Suitable neutral Lewis acids include SbF₅, Ar₃B (wherein Ar is aryl), and BF₃. By a cationic Lewis acid is meant a cation with a positive charge such as Ag⁺, H⁺ and Na⁺.

In many of those instances in which the transition metal compound does not contain an alkyl or hydride group already bonded to the metal, the neutral Lewis acid or a cationic Lewis or Bronsted acid also alkylates or adds a hydride to the metal, i.e., causes an alkyl group or hydride to become bonded to the metal atom, or a separate (from W) compound is added to add the alkyl or hydride group.

A preferred neutral Lewis acid, which can alkylate the metal, is a selected alkyl aluminum compound, such as R^9_3Al , R^9_2AlCl , R^9AlCl_2 , $(R^9AlCl)_2O$, and " R^9AlO " (alkylaluminoxanes), wherein R^9 is alkyl containing 1 to 25 carbon atoms, preferably 1 to 4 carbon atoms. Suitable alkyl aluminum compounds include methylaluminoxane (which is an oligomer with the general formula $[MeAlO]_n$), $(C_2H_5)_2AlCl$, $C_2H_5AlCl_2$, $[(CH_3)_2CHCH_2AlCl]_2O$, and $[(CH_3)_2CHCH_2]_3Al$. Metal hydrides such as $NaBH_4$ may be used to bond hydride groups to the metal M.


For (IV) through (VII) preferred formulas and compounds (as ligands for polymerization catalysts) are found in previously incorporated US5880241, US6103658 and WO00/06620, and preferred grouping and compounds in this publication are also preferred herein. However the compound numbers and group (i.e., R^x) numbers in these publications may vary from those herein, but they are readily convertible. These publications also describes synthesis of the various ligands.

A particularly preferred ligand is an alpha-diimine ligand, and especially ligand (IV). In (IV) is it preferred that R^{14} and R^{15} taken together are an acenaphthene moiety.

There are many different ways of preparing active polymerization catalysts of transition metal coordination compounds of compounds as described herein, many of which are described in previously incorporated US5714556, US5880241, US6103658 and WO00/06620, and those so described are applicable herein. "Pure" compounds which themselves may be ac-

tive polymerization catalysts may be used, or the active polymerization catalyst may be prepared in situ by a variety of methods.

For instance, olefins may be polymerized by contacting, at a temperature of about -100°C to about $+200^{\circ}\text{C}$ a first compound W, which is a neutral Lewis acid capable of abstracting an anion to form a weakly coordinating anion; or a cationic Lewis or Bronsted acid whose counterion is a weakly coordinating anion; a second compound such as



10

and one or more polymerizable olefins wherein:

M is an appropriate transition metal;

R^{13} through R^{16} are as defined above,

Q is a monoanion, preferably alkyl, hydride, chloride, iodide, or bromide; and

S is a monoanion, preferably alkyl, hydride, chloride, iodide, or bromide.

In this instance it is preferred that W is an alkyl aluminum compound. Other methods for preparing active polymerization catalyst will be found in previously incorporated US5714556, US5880241, US6103658 and WO00/06620, and in the Examples herein.

Which active polymerization catalysts will polymerize which olefins (not all catalysts will polymerize all olefins or combinations of olefins) will also be found in previously incorporated US5714556, US5880241, US6103658 and WO00/06620. Monomers useful herein include ethylene, propylene, other α -olefins of the formula $\text{R}^{150}\text{CH}=\text{CH}_2$, wherein R^{150} is n-alkyl containing 2 to about 20 carbon atoms, cyclopentene, a styrene,

and a norbornene. Preferred monomers are ethylene, propylene and cyclopentene, and ethylene is especially preferred.

For all polymerization catalysts, where applicable, nickel is a preferred transition metal.

5 One of the CTAs herein is (I), which is 1,4-cyclohexadiene or one of its derivatives. Useful compounds (I) include the compound in which:

R^1 , R^2 , R^3 , R^4 , R^5 and R^6 are all hydrogen;

one or two of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is alkyl, more
10 preferably alkyl containing 1 to 4 carbon atoms, and especially preferably methyl, and the rest are hydrogen;

R^1 and R^2 taken together form a benzene ring, and all of R^2 , R^3 , R^4 , R^5 and R^6 are hydrogen (compound is 1,4-dihydronaphthalene); or

15 R^1 and R^2 , and R^4 and R^5 , each pair taken together form a benzene ring, and R^3 and R^6 are hydrogen (compound is 9,10-dihydroanthracene).

Compound (II) is a triarylmethane, that is, a tri-substituted (tertiary) methane containing three aryl substituents. In (II) it is preferred that each R^7 is independently aryl or hydrocarbyl substituted aryl, more preferably aryl, and especially preferably every R^7 is phenyl (compound is triphenylmethane). When R^7 taken together may form a ring, a compound such as 9-phenylfluorene is contemplated.

25 The CTAs are used herein in an "effective amount"; that is, an amount required to lower the molecular weight of the resulting polymer in comparison to a polymer identically produced but without the specified CTA. Like most CTAs, the amount of reduction in polymer molecular weight obtained depends upon the concentration of CTA used, but unlike virtually
30 all other CTAs, it has been surprisingly found that lower concentrations of one of the CTAs used herein may actually result in a lower molecular weight and, vice versa,

higher concentrations may not result in as great a molecular weight reduction. This is clearly evident from many of the Examples herein, for instances comparing Examples 1-3, and Examples 4-6. One useful molar range of CTA to transition metal (such as Ni) in the catalyst is about 1 to about 5
100,000, more preferably about 5 to about 20,000, and especially preferably about 100 to about 1000, depending on the particular polymerization process, the CTA used, and other factors such as the monomer (if it is a gas) pressure. The efficacy of any particular CTA under any set of polymerization process conditions (temperature, catalyst used, monomer(s) used, monomer concentration, etc.) can readily be determined by minimal routine experimentation, using the Examples herein as a starting point, and the desired molecular weight range may be readily reached.

It is also known that the polymerization described herein lead to polymers that have an "abnormal" number and types of branches, see for instance previously incorporated US5714556, US5880241, US6103658 and WO00/06620. For example, in the production of polyethylene a polymer may be produced that has some or a great deal of branches of varying length, sometimes also containing "branches-on-branches". This is in comparison to most polyethylenes made by coordination polymerization which have little or no branching. It has surprisingly been found that the addition of the CTAs herein not only modifies the molecular weight of the polymer, but also usually increases the branching level of the polyolefin, sometimes substantially. Thus these CTAs may also be used to increase the branching level of a polymer made under a certain set of polymerization conditions.

The polymerization processes herein may be run in the presence of various liquids, particularly aprotic organic liquids. The catalyst system, monomer(s), and polymer may

be soluble or insoluble in these liquids, but obviously these liquids should not prevent the polymerization from occurring. Suitable liquids include alkanes, cycloalkanes, selected halogenated hydrocarbons, and aromatic hydrocarbons. Specific useful solvents include hexane, toluene, benzene, heptane, isooctane, methylene chloride, and 1,2,4-trichlorobenzene.

The olefin polymerizations herein may also initially be carried out in the "solid state" by, for instance, supporting the transition metal compound on a substrate such as silica or alumina, activating if necessary it with one or more cocatalysts and contacting it with the olefin(s). Alternatively, the support may first be contacted (reacted) with one or more cocatalysts (if needed) such as an alkylaluminum compound, and then contacted with an appropriate transition metal compound. The support may also be able to take the place of a Lewis or Bronsted acid, for instance an acidic clay such as montmorillonite, if needed. Another method of making a supported catalyst is to start a polymerization or at least make a transition metal complex of another olefin or oligomer of an olefin such as cyclopentene on a support such as silica or alumina. These "heterogeneous" catalysts may be used to catalyze polymerization in the gas phase or the liquid phase. By gas phase is meant that a gaseous olefin is transported to contact with the catalyst particle.

More than one (transition metal containing) polymerization catalyst may be present in the process. These catalysts include early metal containing polymerization catalysts such as Ziegler-Natta-type and metallocene-type catalysts as well as later metal transition catalysts. At least one (and optionally more than one) late metal transition catalyst as described above must be present, but other types

of late transition metal containing catalysts may also be present. See, for example, previously incorporated US5880241, as well as US5955555, WO99/10391, WO97/38024, WO97/48735, WO98/38228, WO99/46302 and WO99/50318, also incorporated by reference herein for all purposes as if fully set forth.

In all of the polymerization processes described herein oligomers and polymers of the various olefins are made. These oligomers or polymers may be homooligomers or homopolymers, or cooligomers or copolymers, or a combination of both, depending on which and how many olefins polymerization catalysts are present in the polymerization process. They may range in molecular weight from oligomeric olefins, to lower molecular weight oils and waxes, to higher molecular weight polyolefins. One preferred product is a polymer with a degree of polymerization (DP) of about 10 or more, preferably about 40 or more. By "DP" is meant the average number of repeat (monomer) units in a polymer molecule.

Depending on their properties, the polymers made by the processes described herein are useful in many ways. For instance if they are thermoplastics, they may be used as molding resins, for extrusion, films, etc. If they are elastomeric, they may be used as elastomers. If they are lower viscosity liquids they may be used as lubricants.

Depending on the process conditions used and the polymerization catalyst system chosen, polymers, even those made from the same monomer(s) may have varying properties. Some of the properties that may change are molecular weight and molecular weight distribution, crystallinity, melting point, and glass transition temperature. Except for molecular weight and molecular weight distribution, branching can affect all the other properties mentioned, and branching may



be varied (using the same transition metal compound) using methods described in previously incorporated US5880241.


In the Examples except where noted all pressures are gauge pressures. The following abbreviations are used:

- 5 CHD - 1,4-cyclohexadiene
 GPC - gel permeation chromatography
 MI - melt index (at 190°C and a weight of 2160 g)
 Mn - number average molecular weight
 Mw - weight average molecular weight
 10 PE - polyethylene
 Tm - melting point


In the Examples condensed materials were handled in a nitrogen-purged glove box. Ethylene (Research Grade, 99.5%) and nitrogen (99.998%) were supplied by MG Industries. Heptane, isooctane, and dichloromethane (anhydrous, Aldrich Chemical Co. Milwaukee, Wisconsin, U.S.A.) were filtered through basic alumina (activity I). 1,4-Cyclohexadiene (97%, Aldrich Chemical Co. Milwaukee, Wisconsin, U.S.A.) was filtered through basic alumina (activity I). Modified methylaluminoxane-type 7, MMAO-7 (12.8 wt % Al in Isopar[®] E isoparaffin solvent from Exxon Corp. with a boiling point range of 118-137°C, and a specific gravity of 0.722) was supplied by Akzo Nobel.

The polymerizations were carried out using various late transition metal compounds, made according to procedures described in previously incorporated US5880241. They were:






(XI)



(XII)



(XIII)

5

Examples 1-16 and Comparative Examples A-K

General Polymerization Procedure

A 600 mL pressure reactor equipped with a stirrer (600 rpm) and a 30 mL addition cylinder was used for the ethylene slurry polymerizations. The reactor was dried and purged at 130°C by cycling between nitrogen (1.72 MPa) and vacuum (800 Pa absolute) three times, then cooled to ambient temperature under nitrogen (1.72 MPa).

MMAO-7 (0.6 mL, 2.3 mmol Al) and 1,4-cyclohexadiene were dissolved in heptane (300 mL) in a glass bottle and sealed with a septum. The charging cannula from the reactor was back purged using the nitrogen and inserted into the glass bottle. An ethylene make-up gas line (14 kPa) was inserted into the glass bottle, the reactor was evacuated, and the heptane solution was charged to the reactor under ethylene. The reactor was equilibrated at the desired temperature and ethylene pressure. (XII) was dissolved in dichlo-

15

20

romethane (10 mL) in a glass vial, activated by addition of MMAO-7 (0.1 mL, 0.4 mmol Al), and the vial was sealed with a septum. The charging cannula from the addition cylinder was back purged using nitrogen and inserted into the vial. A
5 nitrogen make-up gas line (14 kPa) was inserted into the vial. The addition cylinder was evacuated and the catalyst solution was charged to the addition cylinder under nitrogen.

The ethylene polymerization was initiated by charging
10 the catalyst solution to the reactor using a slight over-pressure of nitrogen. The ethylene uptake was monitored by measuring the pressure drop from a gas reservoir. The polymerization was terminated by injecting methanol from the addition cylinder. The polyethylene was collected by vacuum
15 filtration, washed with methanol, and dried at 70°C in a nitrogen-purged vacuum oven.

Example 1

This example demonstrates the activation of the catalyst in solution prior to charging to the polymerization reactor.
20

MMAO-7 (0.6 mL, 2.3 mmol Al) and 1,4-cyclohexadiene (1.0 mL, 10.6 mmol, 4400 equivalents per Ni) were dissolved in heptane (300 mL), and charged to the reactor. The reactor was equilibrated to 50°C and 1.24 MPa ethylene. (XII)
25 (1.6 mg, 2.4 μ mol) was dissolved in dichloromethane (10 mL) and activated by addition of MMAO-7 (0.1 mL, 0.4 mmol Al, 1100 total equivalents Al per Ni), then charged to the addition cylinder using nitrogen. The polymerization was initiated by injecting the catalyst solution using nitrogen to
30 bring the final reactor pressure to 1.38 MPa. The temperature rose to an average of 56°C, which was maintained for about 48 min. After quenching with methanol, the PE was

isolated to give 12.63 g (90 kg PE/g Ni). The melt index (190°C, 2160 g) was 0.11 dg/min. The branch content was 38.1 CH₃/1000 CH₂ by ¹H NMR (500 MHz, Cl₂CDCDCl₂, 120°C). The peak melting temperature was 103°C (63 J/g) by DSC on the
5 second heating cycle (heat rate 10°C/min). The molecular weight by GPC (1,2,4-trichlorobenzene, 135°C, universal calibration as PE) was M_w 164,000 with M_w/M_n 2.23.

Tables 1, 2, and 3 summarize the numbered Examples of ethylene slurry polymerizations under various conditions using the General Polymerization Procedure as employed in Example 1. The lettered Comparative Examples followed the same procedure, except that 1,4-cyclohexadiene (CHD) was omitted and hydrogen (or nothing when no CTA was used) was introduced as a gas mixture (mole %) in ethylene. Isooctane
10 was used in place of heptane on some occasions. Table 4 shows results obtained when other nickel complexes were used.

In all the Tables the alkylaluminum compound used was MMAO-7, and the ethylene pressures were 1.38 MPa in Table
20 1, 2.76 MPa in Table 2, and 690 kPa in Tables 3 and 4.

Table 1

Ex.	Ni μ M	Al/Ni Equiv.	CHD Equiv.	Temp. $^{\circ}$ C	Time min	Yield g	Yield kg/g Ni	MI dg/min	Mw	Mw/Mn	Tm, peak $^{\circ}$ C (J/g)	Branching CH ₃ /1000 CH ₂
1	8	1100	4400	56	50	12.63	90	0.11	164,000	2.23	103 (63)	38.1
2	5	1800	14,000	57	50	8.61	98	0.07	204,000	1.96	104 (74)	26.2
3	5	1800	3500	57	30	12.41	140	0.2	154,000	2.07	81 (59)	36.2
4	5	1800	1400	65	30	16.96	190	0.29	128,000	2.3	68, 106 (64)	45.3
5	5	1800	720	65	30	14.3	160	0.72	110,000	1.9	78 (62)	46
6	5	1800	340	65	30	17.66	190	1.02	95,200	1.98	66 (57)	54
A	8	1600	-	50	7	13.34	95	-	429,000	2.63	113 (97)	11
B	8	1600	0.075*	60	15	11.7	83	-	303,000	2.28	113 (93)	17.9
C	8	1600	0.125*	60	12	8.66	61	0.12	179,000	1.92	100 (86)	19.3
D	5	1200	1.9*	68	30	5.6	62	3.7	64,600	2.18	110 (89)	29.2

* Mole percent hydrogen.

Table 2

Ex.	Ni μ M	Al/Ni Equiv.	CHD Equiv.	Temp. $^{\circ}$ C	Time min	Yield g	Yield kg/g Ni	MI dg/min	Mw	Mw/Mn	Tm, peak $^{\circ}$ C (J/g)	Branching CH ₃ /1000 CH ₂
7	5	1800	690	74	30	11.78	130	-	266,000	2.29	114 (90)	19.7
8	6	1600	310	71	30	12.86	130	0.84	90,600	1.93	89 (53)	38.5
E	5	2500	-	52	30	6.06	69	-	395,000	2.35	117 (103)	7.0
F	5	1100	1.0*	72	30	8.89	110	0.66	103,000	2.34	117 (104)	18.9
G	5	1800	1.9*	75	30	8.90	95	2.95	72,300	2.40	120 (118)	17.7

* Mol percent H₂ in ethylene

Table 3

Ex.	Ni μM	Al/Ni Equiv.	CHD Equiv.	Temp. °C	Time min	Yield g	Yield kg/g Ni	MI	Mw	Mw/Mn	Tm, peak °C (J/g)	Branching CH ₃ /1000 CH ₂
9	5	1800	1400	66	30	6.43	140	0.39	127,000	2.37	67, 99(42)	62.5
10	4	2200	880	72	30	8.50	120	6.2	55,700	1.74	30 (30)	83.1
11	4	2200	410	70	30	8.13	110	-	49,400	1.84	31 (39)	94.5
12	5	1800	340 ^a	70	30	10.88	120	7.4	61,800	1.78	38 (36)	80.4
H	5	2500	-	51	21	13.82	157	-	180,000	1.95	84 (43)	29.5
I	5	1300	3*	50	15	7.22	81	0.52	106,000	1.99	98 (97)	27.4
J	5	1300	3*	70	15	1.55	17	-	39,000	1.78	56 (28)	74.0
K	5	1300	13*	70	15	0.66	7	-	18,800	1.72	59(30)	71.3

^a Triphenylmethane. *Mol % H₂ in ethylene.

Table 4

Ex.	Ni Compound	Al/Ni Equiv.	CHD Equiv.	Temp. °C	Time min	Yield g	Yield kg/g Ni	MI	Mw	Mw/Mn	Tm °C (J/g)	Branching CH ₃ /1000 CH ₂
13	(XI)	1900	370	70	30	7.63	92	30	39,200	2.14	58 (34)	63.8
14	(XIII)	1500	300	70	60	6.35	61	0.84	68,500	1.92	-4 (9)	98.4
15	(X)	1900	380	60	60	6.03	73	0.03	235,000	2.2	13 (34)	101.6
16	(IX)	1700	320	70	85	6.03	63	0.03	372,000	2.37	-20 (19)	130.7


CLAIMS

What is claimed is:

1. A process for the polymerization of one or more polymerizable olefins, comprising the step of contacting,
5 under polymerization conditions:

- (a) said one or more polymerizable olefins and
(b) an active polymerization catalyst comprising a complex of a neutral bidentate ligand of a metal selected from the group consisting of nickel, iron
10 and cobalt,

in the presence of an effective amount of a chain transfer, characterized in that the chain transfer agent comprises a compound selected from the group consisting of a compound of the formula (I)




15

and a triarylmethane of the formula R^7_3CH (II), wherein:


each of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently hydrogen, hydrocarbyl, or substituted hydrocarbyl, provided that any two of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 vicinal to one another
20 taken together may form a ring; and

each R^7 is independently aryl or substituted aryl, provided that any two of R^7 taken together may form a ring.


2. The process of claim 1, characterized in that the
25 active polymerization catalyst comprises a nickel, iron or cobalt complex of a ligand of the formula (IV), (V), (VI) or (VII)




(IV)



(V)



(VI)



(VII)

wherein:

R^{13} and R^{16} are each independently hydrocarbyl or substituted hydrocarbyl, provided that the atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R^{14} and R^{15} are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^{14} and R^{15} taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

R^{18} is hydrocarbyl or substituted hydrocarbyl, and R^{20} is hydrogen, hydrocarbyl or substituted hydrocarbyl, or R^{18} and R^{20} taken together form a ring;

R^{19} is hydrocarbyl or substituted hydrocarbyl, and R^{21} is hydrogen, substituted hydrocarbyl or hydrocarbyl, or R^{19} and R^{21} taken together form a ring;

each R^{17} is independently hydrogen, substituted hydrocarbyl or hydrocarbyl, or two of R^{17} taken together form a ring;

R^{22} and R^{23} are each independently hydrocarbyl or substituted hydrocarbyl, provided that the atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R^{24} and R^{25} are each independently hydrogen, hydrocarbyl, or substituted hydrocarbyl;

each R^{26} is independently hydrogen, hydrocarbyl or substituted hydrocarbyl;

R^{27} and R^{30} are independently hydrocarbyl or substituted hydrocarbyl; and

R²⁸ and R²⁹ are each independently hydrogen, hydrocarbyl or substituted hydrocarbyl.

3. The process of claim 1, characterized in that the
5 ligand is an alpha-diimine ligand.

4. The process of claim 1, characterized in that said one or more polymerizable olefins comprises ethylene.

10 5. The process of claim 1, characterized in that the molar ratio of said chain transfer agent to said metal in the active polymerization catalyst is from about 1 to about 100,000.

15 6. The process of claim 1, characterized in that more than one active polymerization catalyst is present.

7. The process of claim 6, characterized in that said more than one active polymerization catalyst is selected
20 from the group consisting of a Ziegler-Natta-type catalyst, a metallocene-type catalyst and another late transition metal containing catalyst.

8. The process of any one of claims 1-7, characterized
25 in that the ligand is the ligand of the formula (IV).

9. The process of any one of claims 1-7, characterized in that the metal of active polymerization catalyst is nickel.

30

10. The process of claim 8, characterized in that the metal of active polymerization catalyst is nickel.

INTERNATIONAL SEARCH REPORT

Inte. n. Application No
PCT/US 00/30773

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 C08F10/00 C08F4/70 C08F4/80 C08F4/26		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 C08F		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data, PAJ		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98 30609 A (COUGHLIN EDWARD BRYAN ;ITTEL STEVEN DALE (US); DU PONT (US); FELDM) 16 July 1998 (1998-07-16) the whole document	1-10
A	WO 97 48735 A (EXXON CHEMICAL PATENTS INC) 24 December 1997 (1997-12-24) cited in the application the whole document	1-10
<input type="checkbox"/> Further documents are listed in the continuation of box C.		
<input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents:		
A document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed		
T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *Z* document member of the same patent family		
Date of the actual completion of the international search <p style="text-align: center;">5 March 2001</p>	Date of mailing of the international search report <p style="text-align: center;">16/03/2001</p>	
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer <p style="text-align: center;">Van Golde, L</p>	

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 00/30773

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9830609 A	16-07-1998	AU 5915098 A	03-08-1998
		BR 9806894 A	21-03-2000
		EP 0952997 A	03-11-1999
		HU 0001341 A	28-07-2000
		JP 2000514132 T	24-10-2000
		NO 993295 A	01-09-1999
		PL 334836 A	27-03-2000
WO 9748735 A	24-12-1997	AU 718884 B	20-04-2000
		AU 3312697 A	07-01-1998
		CA 2258584 A	24-12-1997
		CN 1226257 A	18-08-1999
		EP 1059311 A	13-12-2000
		EP 0906343 A	07-04-1999
		HU 9903930 A	28-03-2000
		JP 2000513399 T	10-10-2000